

1. An aqueous inkjet ink comprising as coloring matter a mixture of about 4% by weight of said ink of Direct Yellow 132 in acid form and about 0.5% to about 1% by weight of said ink of Acid Yellow 17 in acid form.
2. The inkjet ink as in claim 1 in which said Acid Yellow 17 is in amount of about 1% by weight of said ink in acid form.
3. The inkjet ink as in claim 1 in which said ink comprises said Direct Yellow 132, said Acid Yellow 17, a humectant, a penetrant, and water.
4. The inkjet ink as in claim 2 in which said ink comprises said Direct Yellow 132, said Acid Yellow 17, a humectant, a penetrant, and water.